

About Us

Alghanim Industries and French construction giant Saint-Gobain ISOVER join forces together after the recent launch of their new stone wool plant in Yanbu Saudi Arabia and the integration of KIMMCO in Kuwait.

With a 40 year track record in manufacturing, technology and supply of insulation materials and solutions to the Middle East markets, KIMMCO and Saint-Gobain ISOVER now offer their full range of glass wool and stone wool products and solutions under the brand KIMMCO-ISOVER.



- Alghanim Industries is one of the largest privately –owned companies in the Gulf region
- A heritage of over 100 years as a successful commercial enterprise in the Gulf region
- Operations in over 40 countries and employing
- Over 14,000 employees
- A multi-billion dollar company with more than 30 businesses.



World leader in sustainable habitat and construction market.

Saint-Gobain designs, manufactures and distributes material and solution which are key ingredients in the wellbeing of each of us and the future of all.

- Founded in 1665
- Nearly 179,000 employees
- Operates in 67 countries
- Close to 400 patents filed each year

KIMMCO-ISOVER

Rigid Pipe Covering (K450 Plus)

APPLICATIONS

Thermal insulation of steel, copper or plastic pipes operating in temperature up to 232°C (450°F) Fiberglass pipe section faced with ALUGLASS Facing will provide

- A substitute for conventional thermal insulation products that require costly & labour intensive work at site, e.g. Protection of pipe insulation by additional weather proofing.
- An ideal substitute for conventional thermal insulation practices.
- ALUGLASS facing provides factory applied thermal sealing system.

DESCRIPTION

Preformed sections of glass fibers bonded with a heat resistant resin, free from shot and coarse fiber, light, damage resistant, easy to handle, cut and fit. The sections are split along their lengths to provide a hinge for ease of fitting.

Facings

Aluminium Foil / Glass Cloth laminate (ALUGLASS).

Standard Length

1.2m

KRS	kg/m ³	Lbs/ft ³
64	64	4.0
72	72	4.5
80	80	5.0
96	96	6.0
120	120	7.5

Other densities may be available on request.

Silent Features

- K450 plus is faced with factory applied ALUGLASS facing.
- ALUGLASS is aluminium foil laminated with glass fabric.
- It has extremely high Bursting strength of 270 psi i.e. 3 - 4 times higher than that of conventional facings.
- It has extremely high tensile strength of 14.5 KN/m i.e. 3 - 4 times higher than that of conventional facings.
- ALUGLASS is having high mechanical strength, durability and dimensional stability.
- No water vapour can penetrate as ALUGLASS achieves zero water vapour Permeance.
- K450 plus can be used with no additional requirement of handling and weather protection such as application of canvas + vapour barrier.
- K450 plus are rot proof, resist the effects of moisture and will not decompose through continual exposure to the elements.
- K450 plus will not shrink due to the age or temperature variations.
- K450 plus will maintain their thermal properties through the life time of the construction.
- K450 plus are compatible to direct painting. Recommended to use only anti-fungal and anti-bacterial paints in areas where services are exposed like malls, exhibition centres etc. for aesthetic finish. This will save costly metallic cladding.

PIPE SIZES

STEEL PIPES TO BS 1387, BS 3600 AND ANSI / ASTM B 36.10 -1985

PIPE SIZE				NOMINAL WALL THICKNESS															
NOM.BORE		O.D.		mm	20	25	30	40	50	60	75	100							
mm	inch	mm	inch	inch	3/4	1	1 1/4	1 1/2	2	2 1/2	3	4							
10	3/8	17	11/16	*	*	*	*	*	*	*	*	*							
15	1/2	21	27/32	*	*	*	*	*	*	*	*	*							
20	3/4	27	1 1/16	*	*	*	*	*	*	*	*	*							
25	1	34	1 11/32	*	*	*	*	*	*	*	*	*							
32	1 1/4	42	1 11/16	*	*	*	*	*	*	*	*	*							
40	1 1/2	48	1 29/32	*	*	*	*	*	*	*	*	*							
50	2	60	2 3/8	*	*	*	*	*	*	*	*	*							
65	2 1/2	76	3	*	*	*	*	*	*	*	*	*							
80	3	89	3 1/2	*	*	*	*	*	*	*	*	*							
90	3 1/2	102	4	*	*	*	*	*	*	*	*	*							
100	4	114	4 1/2	-	*	*	*	*	*	*	*	*							
114	4 1/2	127	5	-	*	*	*	*	*	*	*	*							
125	5	140	5 1/2	-	*	*	*	*	*	*	*	*							
150	6	166	6 1/2	-	*	*	*	*	*	*	*	*							
200	8	219	8 5/8	-	*	*	*	*	*	*	*	*							
250	10	273	10 3/4	-	*	*	*	*	*	*	*	*							
300	12	324	12 3/4	-	*	*	*	*	*	*	*	*							
350	14	356	14	-	*	*	*	*	*	*	*	*							
400	16	406	16	-	*	*	*	*	*	*	*	*							
450	18	457	18	-	*	*	*	*	*	*	*	*							
500	20	508	20	-	*	*	*	*	*	*	*	*							
550	22	559	22	-	*	*	*	*	*	*	*	*							
600	24	610	24	-	*	*	*	*	*	*	*	*							
Up to	36	914	36	-	*	*	*	*	*	*	*	*							

COPPER TUBES TO BS 2871, ASTM B88M

PIPE SIZE				NOMINAL WALL THICKNESS															
NOM.BORE		O.D.		mm	20	25	30	40	50	60	75	100							
mm	inch	mm	inch	inch	3/4	1	1 1/4	1 1/2	2	2 1/2	3	4							
-	1/2	15	0.596	*	*	*	*	*	*	*	*	*							
-	3/4	22	0.846	*	*	*	*	*	*	*	*	*							
-	1	28	1.112	*	*	*	*	*	*	*	*	*							
-	1 1/4	35	1.362	*	*	*	*	*	*	*	*	*							
-	1 1/2	42	1.612	*	*	*	*	*	*	*	*	*							
-	2	54	2.128	*	*	*	*	*	*	*	*	*							
-	2 1/2	67	2.628	*	*	*	*	*	*	*	*	*							
-	3	76	3.000	*	*	*	*	*	*	*	*	*							
-	3	80	3.144	*	*	*	*	*	*	*	*	*							
-	3 1/2	93	3.660	-	*	*	*	*	*	*	*	*							
-	4	108/105	4.184	-	*	*	*	*	*	*	*	*							
-	5	133/130	5.184	-	*	*	*	*	*	*	*	*							
-	6	159/156	6.208	-	*	*	*	*	*	*	*	*							

Up to 12 inch

Note: Steel & Copper Pipes

1. Other thickness and bores subject to special enquiry.
2. The section thickness is nominal radial thickness subject to manufacturing tolerance and is exclusive of surface finish.

RECOMMENDED THICKNESS

Chilled Pipes

Condensation may take place on piping with temperature below ambient, when sufficient moisture is present in the air. To prevent condensation occurring within the thickness of the insulation, it is necessary to provide vapour check to the warm surface of the insulation. Recommended minimum wall thicknesses of glass fiber pipe insulation for chilled cold water supplies, with vapor barrier applied, are given below:

Pipe Temperature		Ambient Conditions 90% R.H. & 25 °C			
°F	°C	Pipe Sizes		Thickness of Pipe Covering	
		inch	mm	inch	mm
35 - 49	1.5 - 9	Up to 2	Up to 50	1.5	40
		2 1/2 - 14	60 - 350	2.5	60
50 - 70	10 - 21	Up to 3/4	Up to 20	1	25
		1 - 14	25 - 350	1.5	40

Heated Pipes

Recommended minimum thickness of K450 plus for process pipe work. Extracted from table 15 of BS 5422. Thicknesses given are nearest commercial thicknesses higher than those given in the original table. For thickness over 100 mm, multiple layering should be used with staggered joints.

Nom. Bore (mm)	O.D. (mm)	Thickness (mm)	
		100 °C	200 °C
10	17	25	40
15	21	25	50
20	27	30	50
32	42	40	60
40	48	40	60
50	60	50	60
65	76	50	70
80	89	50	75
90	102	50	80
100	114	55	80
150	168	60	90
250	273	70	100
300	324	70	110

PERFORMANCE

Thermal Conductivity

Test in accordance with ASTM C335.

Mean Temperature	Thermal Conductivity in W/m.K for the following densities in kg/m ³				
°C	64	72	80	96	120
10	0.029	0.029	0.030	0.031	0.032
25	0.030	0.030	0.032	0.032	0.033
50	0.032	0.032	0.033	0.035	0.036
100	0.040	0.041	0.039	0.038	0.039
150	0.050	0.050	0.047	0.044	0.045

Mean Temperature	Thermal Conductivity in BTU.in/ft ² h.F for the densities in lbs/ft ³				
°F	4.0	4.5	5.0	6.0	7.5
50	0.205	0.205	0.210	0.210	0.225
77	0.210	0.210	0.220	0.220	0.232
122	0.225	0.225	0.230	0.240	0.254
212	0.270	0.270	0.270	0.265	0.270
302	0.340	0.340	0.330	0.310	0.317

These are typical values subject to normal manufacturing and testing variances.

No Corrosion

Does not cause or accelerate corrosion of steel, copper or aluminum.

Fire Classification

K450 Plus have been tested and listed by the Underwriters Laboratory according to UL 723, ASTM E 84 (File 9704).

K450 Plus achieves class 1 when tested as per BS 476 part 7.

K450 Plus achieves class 0 when tested as per BS 476 part 6 & 7.

Classification (UL 723)	Unfaced	ALUGLASS
Flame spread	not over 25	not over 25
Smoke developed	not over 50	not over 50

Vapor Permeability

ALUGLASS faced K450 plus comply with ASTM E96 Desiccant Method. Permeance not to exceed zero perms (HH - B -100 B Type 1).

Linear Shrinkage

K450 plus shrinkage is negligible when tested in accordance with ASTM C356.

Specific Heat

837.4 J/kg.K

Flexibility

K450 plus will permit expansion and contractions of the pipe without cracking or shrinking.

CONFORMITY TO STANDARDS

American Standards

ASTM C168, 302, 303, 335, 356, 411, 547 (class 1), 585, 665 § 13.8 & 13.9, 680, 871, 1045, 1104/1104M, 1136 (Type 1&2), 1335, 1338; E 84, 96

UL 723

F.S. HH - B - 100B (type 1), HHH-558B

NFPA 255

ASHRAE 90.1 requirements

British Standards

BS 476 (part 4), 874, 1387, 2871, 2972, 3533, 3600, 3958 (part 4), 5422, 5643, 5970

German Standards

DIN 18165, 52612

ISO

161 (part 1), 274, 4200, 8497, 9229, 9291

TYPICAL INSTALLATION PROCEDURE

A. Straight Pipes

- Make sure the pipe surface to be insulated is clean and dry from dust, oil or grease.
- Apply one coat of adhesive over the pipe surface, as per Adhesive manufacturers Instruction.
- Fix the preformed rigid section by opening snap on side enough to insert over the pipe.
- Press the section all over to achieve bonding between pipe and insulation.
- Keep the over lap over the section.
- Apply a light coat of adhesive on down part of overlap and fix it over the section - take care no wrinkles are formed.
- Wipe out any adhesive spill over by using a dry cotton cloth - make sure the surface is dry off adhesive.
- Fix 75 mm Aluglass Tape preferably UL Listed centric to lap and section surface of long seam and joints between section.
- Press the tape using smooth edged plastic card (used telephone cards also found ok) - make sure there are no wrinkles formed in the process of fixing the tape.
- While fixing the next length make sure a coat of adhesive is applied on any face on either of section of continuous joint.
- Fix Aluglass tape preferably UL Listed equally centered between two sections.

B. Joints at Support Insert

Fix the sections from either side of insert using coat of adhesive at each faces of substrate and make sure the insulation is friction fit.

- Apply Aluglass tape centric to the insert allowing equal tape lap over insulation on both side.

NOTE

Other fixing details for 90 degree bends, flange - joints, valve curves etc are available on request.

Commitment to Quality

Properties of KIMMCO-ISOVER Products

- Excellent thermal performance
- Superior acoustic performance
- Excellent fire safety
- Environmentally friendly: made from abundantly available, non-strategic materials.
- Suitable for a wide variety of applications (flexible, semi-rigid, rigid and extra-rigid)
- Address a variety of performance requirements (wide range of facing materials)
- Easy to cut and install, minimum wastage on-site
- Comparatively light in weight
- Dimensionally stable
- No sagging or settling
- Complies with international standards

Further, we are members of the following industry associations:

- Emirates Green Building Council (EGBC)
- Kuwait Green Building Council (KGBC)
- Qatar Green Building Council (QGBC)
- Singapore Green Building Council (SGBC)
- MASDAR (The Future Build)
- Middle East Mineral wool Insulation Manufacturers Association (MEMIMA)

Our Commitment to the Environment

KIMMCO-ISOVER was selected as the sole insulation supplier and official collaborator with MASDAR city, the world's first zero-carbon, zero-waste city, in Abu Dhabi. We have a strong commitment to the environment, health and safety of our people, and surrounding communities, and actively collaborate with local and international environmental agencies. Further, KIMMCO-ISOVER products help developers achieve green building rating certifications such as LEED, Estidama and QSAS

Our Product Listing & Certification

- DCL
- UL
- CE
- BV
- ABS

Our Commitment to Quality

we have a strong commitment to quality, as recognized by our certification by international bodies such as ISO.



KIMMCO ISOVER
SAINT-GOBAIN

www.kimmco-isover.com

Kuwait Insulating Material Manufacturing Co.
P.O. Box 10042 Shuaiba, 65451 Kuwait