



COMFORT Façade Slab FS

High performance slabs for building insulation



Excellent acoustic insulation

COMFORT Façade Slabs FS provides optimal acoustic performance for better comfort.



Excellent thermal insulation

Low Thermal conductivity (k-value) that provides excellent thermal performance, reducing heat loss for residential and commercial buildings.



Effective fire protection

COMFORT Façade Slab FS are non-combustible and classified A1 Euro-class Reaction to Fire



COMFORT Façade Slab FS

Characteristic	Symbol	Unit	Quantities and measured values	Standard
Description	KIMMCO ISOVER stone wool products are made from volcanic rock - a natural material present in large quantities throughout the earth. These raw materials are natural basalt and dolomite coming from Saudi Arabia, our product is complied with ASTM C612 and EN 13162 standard.			
Thermal Conductivity	T	(°C)	35	EN 12 667 ASTM C518 ASTM C177
	λ	(W/m·K)	0.040 - 0.037	
Density	ρ	(kg/m ³)	30 - 200	EN 1602 ASTM C303
Thickness	t	(mm)	30 – 220	EN 823 ASTM C303
Length and Width	L, W	(m)	1.2 x 0.6	EN 822 ASTM C303
Compressive Strength	CS	(kPa)	0.5 – 50	EN 826 ASTM C165
Reaction to Fire Class	RtF	-	Non-combustible, Euro-class A1 (Un-faced)	EN 13 501-1 ASTM E136
Surface burning Characteristic	SBC	-	Class A	ASTM E84
Specific Thermal Capacity	c	(kJ/kg·K)	~ 1	EN 10 456 ASTM C518
Shot Contents	-	(%)	≤ 25 % from the weight	ASTM C1335
Water Vapour Sorption	-	(%)	< 1 by weight	ASTM C1104
Water Vapour Diffusion Resistance Factor (Un-faced)	μ	-	~ 1	EN 12 086 ASTM E 96
Facing	Aluminium Foil Scrim FS			
Miscellaneous delivery forms	Our products are supplied in polyethylene packing. As mentioned in the MSDS product should be stored in a dry place.			

The technical information corresponds to our present state of knowledge and experience at the date of printing (see imprint). But no legal guarantee can be given, unless it has been explicitly agreed. The state of experience and knowledge is developing continuously. Please see to it that you always use the latest edition of this information. The described product applications do not take special circumstances in consideration. For further information, please contact our team. We deliver only according to our terms of trade and terms of delivery.

www.kimmco-isover.com